

Reemay® Filtration Grade Spunbonded Polyester (Metric)

Style No.	Color	Basis Weight gsm	Thickness mm	Grab Tensile (N) MD X XD	Trap Tear (N) MD X MD	Textext cm <sup>3</sup> /s/cm <sup>2</sup>
<b>Straight Fibers</b>						
2004	natural	13.6	0.12	39 x 29	10 x 13	840
2055W	natural	18.7	0.17	41 x 26	13 x 17	779
2006	natural	20.3	0.18	54 x 39	19 x 24	714
2011	natural	25.4	0.20	96 x 50	22 x 26	610
2014	natural	34.0	0.24	99 x 74	28 x 31	450
2016	white	45.8	0.26	131 x 98	28 x 35	327
2024	white	71.2	0.31	246 x 181	40 x 51	184
2030	white	79.7	0.31	269 x 204	37 x 45	163
2033	white	100.0	0.42	377 x 291	55 x 69	134
2040	white	135.6	0.53	538 x 409	73 x 91	101
2060	white	203.4	0.74	800 x 623	111 x 160	61
2250	natural	17.0	0.12	48 x 33	14 x 19	687
2275	natural	25.4	0.15	71 x 56	20 x 23	474
2200	natural	35.6	0.25	96 x 90	25 x 27	337
2214	natural	45.8	0.22	137 x 124	31 x 34	262
2295	natural	100.0	0.40	343 x 316	93 x 98	131
2817	white	50.9	0.32	N/A	N/A	N/A
<b>Crimped Fiders</b>						
2470	natural	203.4	0.76	578 x 417	142 x 187	90
<b>Antimicrobial</b>						
2530L	blue	96.3	0.47	420 x 160	21 x 170	153
2540L	blue	130.6	0.63	592 x 254	62 x 166	119

Reemay® Calendered Polyeter (Metric)

<b>Flat Bonded</b>						
6125	natural	84.8	0.25	356 x 218	N/A	107
6130	natural	101.7	0.29	438 x 269	N/A	80
6140	natural	136.0	0.356	600 x 467	N/A	45
6230	natural	101.7	0.432	399 x 316	N/A	119
2130L	natural	101.7	0.18	N/A	N/A	9
<b>Sonic Bonded</b>						
7180S	white	282.2	1.194	N/A	N/A	49

## Reemay® 필터 효율

Reemay style	Basis Weight (osy)	Pressure Drop in. H2O	%Retention at Particle Micron Size:					
			0.3-0.5	0.5-0.7	0.7-1.0	1.0-2.0	2.0-3.0	3.0-5.0
<b>Straight fibers</b>								
2004	0.4	0.4	0.3	1.4	2.2	2.8	3.3	4.8
2055W	0.55	0.55	0.3	1.4	2.5	4.4	10.0	18.9
2006	0.6	0.6	0.3	0.1	3.1	4.7	8.0	12.8
2011	0.75	0.75	0.6	1.5	2.2	3.0	9.8	14.5
2014B	1.0	1.0	0.5	1.2	2.4	8.3	15.2	21.9
2016	1.35	1.35	0.9	1.3	5.8	13.1	23.9	34.0
2024	2.1	2.1	1.4	5.6	14.3	29.5	52.1	63.0
2033	2.95	2.95	4.0	11.7	24.0	43.1	64.9	71.3
2040	4.0	4.0	3.9	16.2	33.7	57.1	77.0	82.4
2250	0.5	0.5	0.2	0.3	0.4	3.1	5.2	8.6
2275	0.75	0.75	0.4	1.0	1.8	3.9	10.8	16.7
2200	1.05	1.05	1.1	1.6	2.2	9.4	18.2	21.4
2214	1.35	1.35	0.8	4.5	9.0	19.4	36.4	40.5
2295	2.95	2.95	1.8	10.1	21.9	38.7	56.7	58.0
2817	1.5	1.5	2.9	5.1	9.6	18.1	36.1	44.2
<b>Crimped Fibers</b>								
2470	6.0	0.41	4.8	18.8	35.2	50.6	62.9	64.8
<b>Synergex Composite Media</b>								
6125	2.5	0.31	2.9	18.0	34.7	47.5	55.6	56.8
6130	3.0	0.43	10.4	31.7	46.7	58.8	63.9	66.7
6140	4.0	0.56	14.9	39.8	60.5	73.0	78.9	80.4
6230	3.0	0.27	10.1	23.1	38.2	53.9	65.8	67.9